

TECHNICAL DETAILS

Cork origin	Sardinia, Italy
Diameter, tolerance	± 0,4 mm
Height, tolerance	± 0,5 mm
Ovality	< 0,5 mm
Density	160 kg / m ³
Humidity, range	4 – 8 %
Capillarity	< 10 mm
Powders and peroxide release	NO
Uncorking strength, range	15 – 45 daN
Sensorial analysis	Absence of anomalous or moulds odours
Diameter recovery after compression	85% after 1'; 90% after 1 hr
Stamp (if requested)	Fire-branding
Lubrication (if requested)	Polymerized silicon. FDA approved – no solvents
Packaging	Polyethylene vacuum bags, in cartons

SUGHERIFICIO SARGALESE s.n.c.

Sede produttiva: Zona Industriale Alta Gallura - 07029 Tempio Pausania (SS), Italy
 Sede legale: Via Mazzini 15/A - 07023 Calangianus (SS), Italy
e-mail: info@sargalese.it - www.sargalese.it